

Halar® 500LC

chlorotrifluoroethylene polyethylene

General

| | | | |
|-------------------|--|-----------------------------|-----------------|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • North America | • South America |
| Features | • Low Viscosity | | |
| Uses | • Wire & Cable Applications | | |
| Forms | • Pellets | | |
| Processing Method | • Extrusion | • Injection Molding | |

Physical

| | Typical Value | Unit | Test Method |
|---|---------------|----------|-------------|
| Specific Gravity | 1.68 | | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (275°C/2.16 kg) | 18 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow | 0.025 | in/in | ASTM D955 |
| Water Absorption (Equilibrium) | < 0.10 | % | ASTM D570 |

Mechanical

| | Typical Value | Unit | Test Method |
|---------------------------------------|---------------|------|-------------|
| Tensile Modulus ¹ (73°F) | 240000 | psi | ASTM D638 |
| Tensile Strength ¹ | | | ASTM D638 |
| Yield, 73°F | 4350 | psi | |
| Break, 73°F | 6820 | psi | |
| Tensile Elongation ¹ | | | ASTM D638 |
| Yield, 73°F | 5.0 | % | |
| Break, 73°F | 250 | % | |
| Flexural Modulus ² (73°F) | 245000 | psi | ASTM D790 |
| Flexural Strength ² (73°F) | 6820 | psi | ASTM D790 |
| Coefficient of Friction | | | ASTM D1894 |
| vs. Itself - Dynamic | 0.20 | | |
| vs. Itself - Static | 0.20 | | |
| Taber Abrasion Resistance | | | |
| 1000 Cycles, 500 g, CS-17 Wheel | 5.00 | mg | |

Impact

| | Typical Value | Unit | Test Method |
|---------------------|---------------|----------|-------------|
| Notched Izod Impact | | | ASTM D256 |
| -40°F, 0.126 in | 3.9 | ft·lb/in | |
| 73°F, 0.126 in | No Break | | |

Hardness

| | Typical Value | Unit | Test Method |
|------------------------------|---------------|------|-------------|
| Rockwell Hardness (R-Scale) | 90 | | ASTM D785 |
| Durometer Hardness (Shore D) | 75 | | ASTM D2240 |

Thermal

| | Typical Value | Unit | Test Method |
|--|---------------|------|-------------|
| Deflection Temperature Under Load | | | ASTM D648 |
| 66 psi, Unannealed | 194 | °F | |
| 264 psi, Unannealed | 149 | °F | |
| Brittleness Temperature | < -105 | °F | ASTM D746A |
| Glass Transition Temperature | 185 | °F | DMA |
| Melting Temperature | 468 | °F | ASTM D3418 |
| Peak Crystallization Temperature (DSC) | 432 | °F | ASTM D3418 |

| Thermal | Typical Value | Unit | Test Method |
|--|---------------|-------------------------------|-------------|
| CLTE - Flow | 0.000056 | in/in/°F | ASTM D696 |
| Specific Heat (73°F) | 0.230 | Btu/lb/°F | ASTM D3418 |
| Thermal Conductivity (104°F) | 1.0 | Btu-in/hr/ft ² /°F | ASTM C177 |
| Crystallization Heat | 40.0 | J/g | ASTM D3418 |
| Heat of Fusion | 42.0 | J/g | ASTM D3418 |
| Thermal Stability - 1% mass loss, N ₂ | 761 | °F | TGA |
| Electrical | Typical Value | Unit | Test Method |
| Volume Resistivity ³ (73°F) | 5.5E+16 | ohm·cm | ASTM D257 |
| Dielectric Strength (73°F, 0.126 in) | 360 | V/mil | ASTM D149 |
| Dielectric Constant (73°F, 1 MHz) | 2.57 | | ASTM D150 |
| Flammability | Typical Value | Unit | Test Method |
| Flame Rating - UL | V-0 | | UL 94 |
| Oxygen Index | 52 | % | ASTM D2863 |

Notes

Typical properties: these are not to be construed as specifications.

¹ 2.0 in/min

² 0.098 in/min

³ 50% RH

www.SolvaySpecialtyPolymers.com

Contact Solvay Specialty Polymers

Europe, Middle East and Africa SpecialtyPolymers.EMEA@solvay.com
Americas SpecialtyPolymers.Americas@solvay.com
Asia and Australia SpecialtyPolymers.Asia@solvay.com

For assistance with an emergency involving this product, such as spill, leak, fire or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590
International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300
+1.703.527.3887 (CHEMTREC)
Europe +44.208.762.8322 (CARECHEM)
China +86.10.5100.3039
All other Asian countries +65.633.44.177

For additional product information, technical assistance and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557 / +1.770.772.8760
Europe +49.211.5135.9000
Japan +81.3.5425.4300
China & Southeast Asia +86.21.5080.5080

Material Safety Data Sheets (MSDS) for products of Solvay Specialty Polymers are available upon request from your sales representative or by emailing us at specialtypolymers@solvay.com. Always consult the appropriate MSDS before using any of our products.

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanaplast companies along with the Ixan® and Diofan® PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.
© 2012 Solvay Specialty Polymers. All rights reserved.

