



Polypropylene Bormed™ HF840MO

Description

Bormed HF840MO is a resin intended for evaluation for use in Healthcare applications.

Bormed HF840MO is a polypropylene homopolymer modified with an internal lubricant and typically used in injection moulding. It is characterized by a good processability and an easy de-moulding. Products produced from Bormed HF840MO are characterised by a controlled low friction, good physical properties and low warpage because of the narrow molecular distribution. Bormed HF840MO can be sterilised with ethylene oxide or steam.

Applications

Bormed HF840MO has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of Bormed HF840MO .

Disposable syringe barrels
Needle cover
Catheter connections

Aerosol valves
Closures

This grade may only be used for the applications listed in the Product Datasheet and only to the extent that the application is within the scope of the tests set out in the Statement on Compliance to Regulations on Medical Use for that grade. If an application is not listed in the Product Datasheet, the grade can be used for such application only after express written consent of the Borealis Marketing Manager, Healthcare. Borealis prohibits the use of any healthcare grade product in an implantable device that is introduced into the human body by surgical intervention and that is intended to remain in place following surgical procedure.

Special features

Easy processing
Low friction

Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	19 g/10min	ISO 1133
Flexural Modulus	1.250 MPa	ISO 178
Tensile Modulus (1 mm/min)	1.250 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	11 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	29,5 MPa	ISO 527-2
Heat Deflection Temperature (0,45 MPa) ¹	85 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	3,5 kJ/m ²	ISO 179/1eA

¹ Measured on injection moulded specimens acc. to ISO 1873-2

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Bormed HF840MO

Processing Techniques

This product is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature	210 - 260 °C	
Holding pressure	200 - 500 bar	Minimum to avoid sink marks.
Mould temperature	30 - 40 °C	
Injection speed	Medium to high	

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

Storage

Bormed HF840MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

- Recovery and disposal of polyolefins
- Information on emissions from processing and fires
- "Safety data sheet" / "Product safety information sheet"
- Statement on compliance to regulations on medical use
- Statement on compliance to food contact regulations
- Statement on chemicals, regulations and standards
- Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd.
 Head Office Tel. +85-2-6957-5415
 Research Center Tel.+188 1699 6168



Polypropylene
Bormed HF840MO

Disclaimer

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168