

ExxonMobil™ PP9574E6

Polypropylene Random Copolymer

Product Description

A highly clarified random copolymer resin designed for general purpose injection molding applications requiring resistance to buildup of static electricity.

General

Availability ¹	▪ North America
Features	<ul style="list-style-type: none"> ▪ Antistatic ▪ Controlled Rheology ▪ Ethylene Oxide Sterilizable ▪ High Clarity
Uses	<ul style="list-style-type: none"> ▪ Caps ▪ Closures ▪ Medical/Healthcare Applications ² ▪ Packaging ▪ Rigid Packaging
Appearance	▪ Natural Color
Form(s)	▪ Pellets
Processing Method	▪ Injection Molding
Revision Date	▪ 11/01/2010

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield			ASTM D638
2.0 in/min (51 mm/min)	4140 psi	28.5 MPa	
Elongation at Yield (2.0 in/min (51 mm/min))	13 %	13 %	ASTM D638
Flexural Modulus - 1% Secant			
0.051 in/min (1.3 mm/min)	144000 psi	993 MPa	ASTM D790A
0.51 in/min (13 mm/min)	177000 psi	1220 MPa	ASTM D790B

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	1.6 ft·lb/in	88 J/m	ASTM D256A

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	169 °F	76.2 °C	ASTM D648

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Rockwell Hardness	84	84	ASTM D785

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.